

MATERIAL SAFETY DATA SHEET

EVENCURE XDS

COMPANY DETAILS

Page 1 of 2

Name: Evenrange Australia,
Address: 12 Frankston Gardens Dve., CARRUM DOWNS. Vic 3201
Phone: (03) 9782 3233
Fax: (03) 9782 3244

IDENTIFICATION

Product Name:	EVENCURE XDS	U.N. Number:	N/A
Shipping Name:	N/A	Dangerous Goods Class:	N/A
Subsidiary Risk:	N/A	Hazchem Code:	N/A
Poisons Schedule:	5	Packaging Group:	N/A

Chemical Description: Emulsion of resin and low aromatic solvent in water.

Use: Concrete curing compound.

PHYSICAL DESCRIPTION / PROPERTIES

Appearance:	Milky homogeneous liquid or with red fugitive dye	Flammability Limit (%):	See Fire/ Explosion Hazard
Solubility in water (g/l):	Emulsifies	In organic solvents:	Part Soluble
Boiling Point:	100-196°C	Vapour Pressure @25°C:	NAS
pH:	7	Relative Density:	0.98
Volatiles (%):	10% hydrocarbon, 70% water	Shelf Life:	12 months
Flash Point (°C):	84°C	Other properties:	NAS

INGREDIENTS

Chemical Entity	CAS Number	Proportion %
Hydrocarbon liquid	64742-89-7	Low approximately 10% WW
Hydrocarbon resin	68131-77-1	20-40%

Due to composition or concentration, all other ingredients exempted from HN and MRC Standard for Uniform Scheduling of Drugs and Poisons and TLV-Worksafe Australia.

HEALTH HAZARD INFORMATION

HEALTH EFFECTS

Acute:	Swallowed: Slight irritant
	Eye: Moderate irritant
	Skin: Slight skin irritant
	Inhaled: Irritant, causes dizziness, loss of consciousness.

**Chronic:
FIRST AID**

Swallowed: Do not induce vomiting. Give glass of water. Contact a doctor or Poisons Information Centre.

Eye: Remove contact lenses. While holding eyes open gently flush with water for 15 minutes. Promptly obtain medical aid.

Skin: Remove contaminated clothes. Wash before re-use. Wash contaminated skin well with soap and water.

Inhaled: Remove to fresh air. Avoid becoming a casualty. Apply artificial respiration if breathing stopped. Seek medical aid. Ensure availability of clean water for eye/skin wash.

First Aid Facility: Ensure availability of clean water for eye/skin wash.

Advice to Doctor: Treat symptomatically.

PRECAUTIONS FOR USE

Exposure Standards: See ingredients, page 1.

Engineering Controls:

Ventilation: Using non-ignitive equipment assure positive ventilation or suitable breathing equipment, *for example*, 3M Model 8712, to maintain vapour levels below TLV-TWA.

Personal Protection: Gloves Long Impervious: YES Overalls: YES
Eye Protection: YES

Flammability: N/A Flashpoint 84°C

SAFE HANDLING INFORMATION

Storage and Transport: Avoid heat, flames, oxidising agents

Spills: Wear appropriate personal protection and ensure adequate ventilation.

Sweep up first: YES
Wash down with detergent/water: YES
Absorb in dry inert material: YES

Disposal: *Observe all Federal, State and Local regulations.*

Fire/Explosion Hazard: Explosion Limit - upper:lower NAS
Dust explosion hazard: N/A
Hazardous decomposition products: NAS
Hazardous polymerisation products/reaction Unlikely
Extinguishing medium Foam CO₂
Firefighters should wear self contained breathing apparatus in enclosed areas.

CONTACT POINTS

ORGANISATION	LOCATION	TELEPHONE
Evenrange Australia	12 Frankston Gardens Dve., CARRUM DOWNS. Vic 3201 ,	(03) 9782 3233 Business Hours (03) 5998 7711 After Hours 0417 346 280 All Hours

All information contained in this Data Sheet is as accurate and up to date as possible. No warranty expressed or implied is made as to its accuracy, reliability or completeness.



VOC Content Test Certificate

Thursday July 23rd, 2009

Manufacturer: Evenrange Australia (12 Frankston Gardens Drive, Carrum Downs Victoria 3201)

Sample Description: Evencure XDS concrete curing and sealant

Date Tested: July 2009 (Tested by FORAY Laboratories – NATA Accreditation 1231)

Test Method: SCAQMD Method 304-91 Determination of Volatile Organic Compounds (VOC) in Various Materials as referenced by South Coast Air Quality Management Division (SCAQMD) Rule 1168.

Test Data:

Specification Green Building Council of Australia Green Star Office Design V2 IEQ-13 Green Star Office Interiors V1.1 IEQ-11	Evencure XDS
Architectural Sealant 250 grams per Litre as VOC content material	87 gram per Litre as VOC content material
Specification Green Building Council of Australia Green Star Office Design V3 IEQ-13	Evencure XDS
Architectural Sealant 250 grams per Litre as VOC content material	87 gram per Litre as VOC content material

Dr. Vyt Garnys
PhD, BSc(Hons) AIMM, ARACI, ISIAQ
ACA, AIRAH, FMA
Managing Director and Principal Consultant

F0907-22



EVENRANGE EVENCURE
XDS IN ADVANCED STAGES
OF OXODISATION.



THIS SITE IS THE
TUNNEL WALLS AT THE
BORDONIA RAIL
INTERCHANGE FOR
JOHN HOLLAND.

